



PRODUCT INFORMATION

ULTIMEG 2220 SOLVENTLESS IMPREGNATING EPOXY RESIN

GENERAL DESCRIPTION

ULTIMEG 2220 is a solventless, single component, epoxy impregnating resin especially formulated for VPI of traction machines conforming to thermal class 220°C .

The cured product exhibits excellent mechanical and electrical properties throughout its working temperature range together with a high level of performance in its resistance to chemicals and moisture.

APPLICATION

A high performance, zero VOC resin for vacuum pressure impregnation of traction machines

SPECIFICATION

VISCOSITY	Brookfield @ 25°C	45-55 poise
GEL TIME	10 grms @ 165°C	5-10 mins
SPECIFIC GRAVITY	@ 21°C	1.13 - 1.17
SHELF LIFE	@ 20°C	12 months

CURE SCHEDULE

TIME (hours) 12 8 TEMPERATURE (°C) 150 165

To maximise properties a cure of 24 hours @ 150°C or an additional post cure of 8 hours at 180°C is recommended.





<u>ULTIMEG 2220</u>

PROPERTIES OF CURED RESIN

BOND STRENGTH	ASTM D2519	20°C	38kg
		150°C	8.6kg
THERMAL ENDURANCE	ASTM D2307	20,000 hours	220°C
GLASS TRANSITION TEMP	IEC1006	Tg	148°C
DIELECTRIC STRENGTH	ASTM D115	At 50Hz & 20°C	190 kV/mm
	50μm film	At 50Hz & 150°C	100 kV/mm
		24hr water immersion	115 kV/mm
ΤΑΝ θ	IEC 455-2	At 50Hz & 20°C	< 0.005
VOLUME RESISTIVITY	IEC 93	20°C.	10 ¹⁴ Ohm cm
DIELECTRIC CONSTANT	IEC250	At 50Hz	3.7
COMPARITIVE TRACKING	IEC112	Proof test	>550V
INDEX			
THERMAL CONDUCTIVITY	VDE0304		0.2W/mK
SHORE D-HARDNESS	DIN53505	25°C	91

HEALTH AND SAFETY

Refer to Material Safety Data Sheet available.

PACKAGING 5kg, 25kg, 220kg

AEV Limited Issue no. 3 Date: 10.11

NOTE: Due to the introduction of improvements from time to time the right is reserved to supply products that may differ slightly from those illustrated or described in this publication.

Email: aev@aev.co.uk www.aev.co.uk